



SECOVAC 2102

METALIZED STATIC SHIELDING

- ESD Static Shield Film
- Conductive Buried Shield layer between two polymeric plastic layers; exposed surfaces are static dissipative
- Contains no Amines and is N-Octanoic acid free
- Polycarbonate compatible, humidity independent and heat sealable
- Meets the electrical requirements of MIL-PRF-81705E, Type 111

Electrical Properties:

	<u>Test Method</u>	<u>Anti Static Values</u>
Static Decay Rate	FTMS 101C Method 4046.1	<0.03 seconds
Surface Resistivity	ASTM-D-267/ESD S11.31	<10 10 ² ohms/sq.

Physical Properties:

	<u>Test Method</u>	<u>Unit of Measure</u>	<u>Typical Values</u>
Color		Silver	
Thickness		.0031	
Yield		sq in/lb(+/-5%)	8750
Tensile Strength	ASTM D882-83 Method A	psi	MD 6500
Tear Strength (Notched)	ASTM D 1004-66	psi	MD 790
		lbs	
		MD	3.0
		TD	2.5
Burst Strength	FTMS 191 C Method 6122	psi	70
Puncture Strength	FTMS 101 C Method 2065.1	lbs	>10
Heat Seal Strength	ASTMF 1876-72	lbs/width	>16
M.V.T.R	ASTMF F1249	gms @100/90% R.H./100 in ² /24 hrs	

The value shown above was based upon the information supplied to Seco Industries. Products users should make his or her own test to determine the suitability of the information and conclusions therein. No salesperson, representative or agent of Seco industries is authorized to give any guarantee, warranty or make any representation contrary to the above.